

0441.21

## **Krypton MBK**

**SAE 15W-50** 

Fully synthetic lubricant with exceptional performance specific for latest generation 4 stroke motorbike engines.

PAKELO KRYPTON MBK SAE 15W-50 is a special fully synthetic lubricant.

It guarantees exceptional performance, High Viscosity Index obtained with exclusive additives that provide superior detergent, dispersant properties, anti-oxidative, anti-corrosion, anti-wear and anti-foam characteristics.

The product, thanks to the presence in the formulation of fine specially selected synthetic bases, shows superior properties compared to a lubricant formulated with mineral base stocks.

PAKELO KRYPTON MBK SAE 15W-50 provides very high thermal and oxidative resistance; reduces evaporation losses (less volatility of the product) and formation of carbon residues when compared to mineral based product.

PAKELO KRYPTON MBK SAE 15W-50 is specifically formulated for keeping, also at high working temperatures - typical of motorbike application - the best lubrication film, the correct fluency between engine and transmission contacts.

Furthermore, it enables very easy start-ups and idling stability when the engine is still cold.

PAKELO KRYPTON MBK SAE 15W-50 thanks to its special additive package, keeps extremely clean engine parts and guarantees at the same time outstanding anti-wear protection of components such as camshaft and transmission parts working under extreme conditions.

The product is highly recommended also for motorbike engines with wet clutch lubrication. The special formulation of PAKELO KRYPTON MBK SAE 15W-50 guarantees the correct friction coefficient and thus prevents slippage during power transfer.





0441.21

# **Krypton MBK**

**SAE 15W-50** 

#### **Application fields**

PAKELO KRYPTON MBK SAE 15W-50 is specifically studied for four stroke motorbike engines also of the latest generation.

PAKELO KRYPTON MBK series is available in several Viscosity Grades envisaged by SAE J300 Specification.

The choice of suitable Viscosity Grade should be done taking into consideration working conditions and Constructor's recommendations.

#### **Performance levels**

API SN, JASO MA2.

### **Chemical-Physical Characteristics**

| Krypton MBK                  | Method<br>analysis | Unit<br>measure | Value<br>SAE 15W-50 |
|------------------------------|--------------------|-----------------|---------------------|
| Density at 15°C              | ASTM D1298         | kg/l            | 0,857               |
| Kinematic Viscosity at 40°C  | ASTM D445          | cSt             | 137,6               |
| Kinematic Viscosity at 100°C | ASTM D445          | cSt             | 19,5                |
| Viscosity Index              | ASTM D2270         | -               | 162                 |
| C.C.S. Viscosity at -20°C    | ASTM D5293         | сР              | 4.500               |
| T.B.N. (Total Base Number)   | ASTM D2896         | mg(KOH)/g       | 7,7                 |
| Sulphated Ash                | ASTM D874          | % (w/w)         | 0,80                |
| Flash Point (C.O.C.)         | ASTM D92           | °C              | > 220               |
| Pour Point                   | ASTM D97           | °C              | -35                 |

The data just above refer to average values and must not be understood as guaranteed characteristics.

This Technical Data Sheet has been carefully checked to guarantee complete and precise information. However, we do not take any responsibility in case of damages caused by any mistakes or omissions. Due to continual product research and development, the information contained herein is subject to change without notification.

